

TECHNICAL FILE TWINSON

application: P9369

date: 28/10/2016

version: v1

deceuninck

		EN 15534-1	based on	specific property	unit	value	
MATERIAL CHARACTERISTICS COEX	physical properties	density	§ 6.2	ISO 1183-1/A		kg/dm ³ 1.41 ± 0.05	
	durability	resistance to termites	§ 8.4	EN 117		class 1	
		resistance against basidiomycetes	§ 8.5.2	ENV 12038		class 1	
		resistance against soil inhabiting soft rotting micro-fungi	§ 8.5.3	CEN/TS 15083-2		class 1	
PRODUCT RELATED CHARACTERISTICS	physical properties	slip resistance	---	DIN 51130	rifled surface	class R10	
			---	DIN 51130	wood structure	class R11	
	mechanical properties	flexural properties (Lv=50 cm)	§ 7.3.2	EN 310	flexural modulus	MPa	6000 ± 10%
		creep behaviour (Lv=50 cm/85kg/50°C/7 days)	§ 7.4.1	EN 310	bending strength	MPa	> 40
	durability	natural weathering (1 year Bandol)			additional bending	mm	< 10
		cyclic conditions (Lv=50 cm)	§ 8.3.2	EN 321	bending strength retention	%	< 20
		boiling test	§ 8.3.3	ISO 1087-1	bending strength retention	%	< 20
	thermal properties	heat reversion	§ 9.3	EN 479	mass increase	%	< 4
		heat build-up	§ 9.4	ASTM D4803		°C	< 45
		linear thermal expansion (-20 °C ... +60°C)	§ 9.2	ISO 11359-2	length direction	10 ⁻⁶ m ⁻¹ K ⁻¹	20 - 25
	burning behaviour	single flame source	§ 9.6.1	ISO 11925-2	classification EN 13501-1	class	Cfl s1
radiant heat source		§ 9.6.3	ISO 9239-1	classification EN 13501-1	class		

The test results relate only to a sample used by the Deceuninck laboratories. Whilst the Deceuninck laboratories warrant that their tests will meet their applicable declared specifications, the Deceuninck laboratories make no other warranty, expressed or implied and accept no responsibility or liability in respect of false results which are within the limits of the declared specifications of the tests offered. No representation or warranty is given by Deceuninck or any of its officers or employees as to the accuracy of any test methods or test results. Neither Deceuninck nor any of its officers or employees shall have any liability or responsibility in respect of any laboratory or the accuracy of any test methods, test results or reports produced by any Deceuninck laboratory.