## **TECHNICAL FILE TWINSON**

application: O-Wall date: 21/02/2019

P9596 <u>version:</u> v1



|                                    |                          |   | EN 15534-1 | based on       | specific property          | unit                             | value       |
|------------------------------------|--------------------------|---|------------|----------------|----------------------------|----------------------------------|-------------|
| MATERIAL<br>CHARACTERISTICS        | physical properties      | density                                       | § 6.2      | ISO 1183-1/A   |                            | kg/dm³                           | 1.42 ± 0.05 |
|                                    | mechanical<br>properties | flexural properties                           | § 7.3.1    | ISO 178        | flexural modulus           | MPa                              | 5000 ± 10%  |
|                                    |                          |   |            |                | bending strength           | MPa                              | > 55        |
|                                    | durability               | swelling and water<br>absorption<br>(28 days) | § 8.3.1    | EN 317         | mass increase              | %                                | < 8         |
|                                    |                          | resistance to termites                        | § 8.4      | EN 117         |                            | class                            | 1           |
|                                    |                          | resistance against basidiomycetes             | § 8.5.2    | ENV 12038      |                            | class                            | 1           |
|                                    |                          | resistance against soft rotting micro-fungi   | § 8.5.3    | CEN/TS 15083-2 |                            | class                            | 1           |
|                                    | thermal<br>properties    | linear thermal<br>expansion<br>(-20 °C +60°C) | § 9.2      | ISO 11359-2    | length direction           | 10 <sup>-6</sup> K <sup>-1</sup> | 20 - 25     |
|                                    |                          | oxygen index                                  | § 10.1     | ISO 4589-2     |                            | %                                | > 20        |
| PRODUCT RELATED<br>CHARACTERISTICS | durability               | natural weathering<br>(1 year Bandol)         |            |                | bending strength retention | %                                | < 20        |
|                                    |                          | boiling test                                  | § 8.3.3    | ISO 1087-1     | mass increase              | %                                | < 8         |
|                                    | thermal properties       | heat reversion                                | § 9.3      | EN 479         |                            | %                                | < 0.2       |

The test results relate only to a sample used by the Deceuninck laboratories. Whilst the Deceuninck laboratories warrant that their tests will meet their applicable declared specifications, the Deceuninck laboratories make no other warranty, expressed or implied and accept no responsibility or liability in respect of false results which are within the limits of the declared specifications of the tests offered. No representation or warranty is given by Deceuninck or any of its officers or employees as to the accuracy of any test methods or test results. Neither Deceuninck nor any of its officers or employees shall have any liability or responsibility in respect of any laboratory or the accuracy of any test methods, test results or reports produced by any Deceuninck laboratory.